

Eco-Shell

Material Safety Data Sheet

PROPERTIES:

Dual Screen Aggregates have the following characteristics;

SPECIFIC GRAVITY	1.35
pH VALUE AT 25°C (IN WATER)	4-6
FREE MOISTURE (80°C FOR 15HRS)	3-10%
FLASH POINT (CLOSED CUP)	380°
HARDNESS -VICKERS NO	25-30
MOHS SCALE	3-4
DRY PACKING DENSITY (LBS PER CU. FT.)	22-74

GSA Specification: AA-1722, Type 2

Military Specification: MIL-G-5634 Type 3

CHEMICAL ANALYSIS:

Nitrogen	0.10
Cellulose	40/60
Lignin	20/30
Toluene Solubility	0.5/1.0
Methoxyl	6.5
Chlorine	0.10
Ash	1.5
Cutin	1.0